

JOHNS MANVILLE  
RECEIVED  
CENTRAL FAX CENTER

APR 17 2007

Docket No. JM 7343-2  
Application No. 10/736,119  
Page 2**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**LISTING OF CLAIMS:**

1. (Previously Presented) A woven, patterned glass fiber textile fabric comprised of a glass fiber yarn with a titer of from 270 to 300 tex as the warp, and a glass fiber yarn having a titer ranging from 68 to 660 tex as the weft.
2. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is in the range of from about 270 to 290 tex.
3. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 278 tex.
4. (Original) The glass textile fabric of claim 1, wherein the titer of the weft yarn is in the range of from 190 to 350 tex.
5. (Original) The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 200 tex.
6. (Original) The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 330 tex.

Docket No. JM 7343-2  
Application No. 10/736,119  
Page 3

7. (Original) The glass textile fabric of claim 1, wherein the warp density of the textile fabric ranges from 2.5 to 20 threads/cm.

8. (Previously Presented) The glass textile fabric of claim 7, wherein the warp density of the textile fabric is in the range of from about 6 to 10 threads/cm.

9. (Previously Presented) The glass textile fabric of claim 1, wherein the weft yarn density of the textile fabric is in the range of from about 2.0 to 12 threads/cm.

10. (Original) The glass textile fabric of claim 1, wherein the textile is impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.

11-17. (Canceled)